

PURE ASPHALT

MANUFACTURER OF SPECIALTY COATINGS SINCE 1927

PRODUCT DATA

3300 W. 31ST STREET
CHICAGO, IL 60623
PHONE: 773.247.7030
FAX: 773.247.7066
WWW.PUREASPHALT.COM

No. 102 Low V.O.C. PRIMER

DESCRIPTION

No. 102 Low V.O.C. Primer is a single-component, solvent-based bituminous primer especially designed to promote adhesion of the No. 435 Hot-Applied Liquid Membrane by preparing the concrete surface. The No. 102 Low V.O.C. Primer is spray ready without having to thin or can also be applied with a roller.

APPLICATION

Prime all concrete, gypsum, masonry, brick, plywood, and metal surfaces to which the surfaces of peel and stick, sheet membranes and flashings, or No. 9001 EV Hot-Applied Membrane is to be applied. Do not thin Primer before application. No. 102 Low V.O.C. Primer is best applied with airless spray equipment. No. 102 Low V.O.C. Primer can also be applied by roller. Use a screen in the pail to roll off the excess primer. The product has a satisfactory cure when it will not transfer when touched. Apply only to areas to be waterproofed.

COVERAGE

Coverage rate will vary. The following is a guide, but Pure Asphalt Company cannot guarantee coverage rates. The concrete should show a deep stain as opposed to being fully colored black. For smooth, hair broom finish, cover concrete at 500 sq. ft. per gallon. All fluid applied product application rates are based on theoretical coverage relative to the percentage of solids in the material. These are minimum application rates to achieve the required dry film thickness for the system and do not account for substrate condition or porosity. A thicker application of the product may be necessary to achieve the required dry film thickness for the system relative to the substrate.

PACKAGING

Available in 5-gallon pails and 55-gallon drums. 330- Gal Totes available on request.

Warnings and Hazards

Flammable liquid and vapors. Use only with adequate ventilation. Keep liquid and vapors away from open flames. Avoid contact with eyes and skin. In the event of contact, wash off immediately. Wear protective clothing, especially impervious rubber gloves and eye protection. Refer to the SDS for important warnings and product information.

Typical Properties

Property	No. 102 Low V.O.C. Primer
Color	Brownish Black
V.O.C. Content	<250 g/l
Tack- Free Time	1 hr at 77°F
Flash Point	110°F
Corrosivity	None
ASTM D41	Complies