

PRODUCT DATA

3300 W. 31ST STREET CHICAGO, IL 60623 PHONE: 773.247.7030 FAX: 773.247.7066 WWW.PUREASPHALT.COM

Pure Asphalt – 9001 EV Grade

DESCRIPTION

Pure Asphalt – 9001 EV Grade is an environmentally friendly, hot applied, rubberized asphalt formulated to provide a monolithic fully bonded waterproofing membrane. It is hot poured in a single or fabric reinforced application. Pure Asphalt – EV Grade is composed of a specially selected blend of refined asphalts, synthetic rubber and mineral stabilizers and contains at least 20% post consumer recycled content. It is modified with additives to promote adhesion and improve low temperature flexibility.

FEATURES

- Environmentally friendly
- Contains 20% post-consumer recycled content
- May contribute to LEED credits
- Seamless application provides monolithic waterproofing.
- Bridges non-working cracks up to 1/16" in width.
- Full adhesion to deck restricts lateral water movement.
- 100% solids provides immediate cure on cooling.
- Cures very quickly as it cools.

PACKAGING

Pure Asphalt – EV Grade is packaged in standard 35 lbs poly lined boxes. Poly is designed to dissolve in melter.

Pure Asphalt – 9001 EV Grade Physical Properties:

Flash point Solids	ASTM D-92 ASTM D-1353	600 F 100%	Pass
Penetration	CGSB-37.5	80 @ 25 C 155 @ 50 C	Pass Pass
Softening Point	ASTM D-36	83 C, 181 F	Pass
Elongation	ASTM 412		>1000%
Low Temp Flex	CGSB-37.5		Pass
Low Temp Crack Bridging	CGSB-37.5		Pass
Resistance to Acid	50% Nitric, 50% Sulfuric		Pass
Resistance to Water	CGSB-37.5	5 days 50 C	Pass
Water Absorption	CGSB-37.5		.12grams gain
Water Vapor Permeability	ASTM E96		.013 perms
Toughness	CGSB-37.5		12 J
Ratio: Toughness to Peak Load	CGSB-37.5		.060
Viscosity	CGSB-37.5		6 seconds
Adhesion	CGSB-37.5		Pass
Sodium Chloride Resistance	ASTM D-896		Pass
Fertilizer Resistance	ASTM D-896		Pass

The information presented herein is based on the data available and is believed to be correct. However, nothing stated in this bulletin is to be taken as a warranty, expressed or implied regarding the accuracy of the information of the use of our product used singly or in conjunction with other products.